

# TECHNICAL DATA SHEET



## SAKRET FIN Plus – Filler

15 08 25

SAKRET FIN Plus Lime-cement finishing filler for mineral surfaces

- Application:**
- For different kinds of mineral surfaces.
  - For interior works!!!
  - For final levelling before painting and wall-papering.

- Qualities:**
- Good coverage.
  - Easy grinding.

- Components:**
- Portland cement
  - Hydrated lime
  - Inert fillers
  - Technological additives

**Technical data:**

Water to be added for:	1 kg	about 0,350 l
	4 kg	about 1,400 l
Readiness time:	about 5 min.	
Processing time:	about 2 hours	
One layer thickness:	1-3 mm	
Can start grinding:	After 24 hours	
Processing temperature:	from +5°C till +25°C	
Fire safety class	A1 (non-flammable)	

- Foundation preparation:**
- Surface must be dry, firm, without cracks. Surface must be cleaned off less enduring and/or detachable layers, as well as dust, dirt, oil, paint leftovers and other impurities that decrease adhesion.
  - Strongly absorbing mineral surfaces and gyps cardboard shall be primed with **SAKRET BG** or concentrated primer **SAKRET UG**, diluted with water, in proportion 1:3.
  - Loose surfaces must be primed with deep primer **SAKRET TGW**.

- Processing:**
- For preparation of filler the dry mixture shall be mixed in clean container with cold water till homogenous mixture of needed consistency, without lumps, is formed. After 5 minutes readiness time, it shall be mixed repeatedly.
  - The prepared mixture shall be laid on surface with shovel and evenly levelled.
  - Hardened material can be grinded with fine sand paper or grinding sieve!

- Additional recommendations for processing:**
- It is recommended to use mixer with 600 rotations per minute for filler preparation.
  - Material that has started to harden shall not be diluted with water!

- Consumption:**
- Aproximately 1,2 kg/m<sup>2</sup>, if layer thickness is 1 mm

- Packing:**
- Paper bags 4 kg / full pallet 200 pcs.

- Storage:**
- Packing must be kept away from impact of weather conditions, store on wooden pallets in cool and dry place, torn or opened packing must be covered immediately.
  - Storage time in original not opened packing – 12 months.

# TECHNICAL DATA SHEET



## SAKRET FIN Plus – Filler

15 08 25

---

**Utilization:**

- Hardened mixture shall be utilized in compliance with local legislation as construction material of mineral origin.
- Packing shall be utilized in compliance with local legislation demands as paper, laminated with polythene layer.

---

**Safety information:**

- Contains cement, reacts on moisture in alkaline way!
- Contains solvent, six worthy chrome Cr (VI) ions  $\leq 0,0002\%$ .
- Safety signs are on packing and in safety data sheets.

**Additional information:**

- During hardening phase material must be kept away of sun beams, draught, frost and too high temperature ( $>+25^{\circ}\text{C}$ );
- Technical data refer to temperature  $+23\pm 2^{\circ}\text{C}$  and relative air humidity  $50\pm 5\%$ .

Colour	Packing 1	Packing 2	Barcode
White	4 kg	200 pcs. /pal.	4751006560819

The information provided in the technical data sheet refers to the usage of the above product, if there is no other technical documentation, prepared and issued by the producer. The producer is not responsible for losses caused by wrong usage of the given product. In case of questions or uncertainty, please contact producer or seller. Information on product's safety is available in safety data sheets, declared values – in declaration of performance.