## **TECHNICAL DATA SHEET**



## **PORTLANDCEMENT CEM I 42,5 N**

15 09 16

Portland cement for making	building mortars and concrete			
Application:	<ul> <li>For the production of construction mortars, concrete, paving stones, finishing plates, decorative panels, sculptures, joint fillers.</li> </ul>			
Qualities:	<ul><li>High physical-mechanical strength.</li><li>Grey colour.</li></ul>			
Components:	Portland cement.	ortland cement.		
Technical data:	Type in compliance with standard EN 197-1:	CEM I 42,5 N		
	Strength class:	42,5		
	Pressure strength after 2 days:	≥ 10 MPa		
	Pressure strength after 28 days:	≥ 42,5 MPa		
	Binding time:	≥ 60 min.		
	Water-soluble chromium content Cr <sup>6+</sup> :	≤ 2 mg/kg		
Processing:  Additional recommenda-	<ul> <li>Pour cement and fillers into a clean container or concrete mixer, mix with cold, clean water until a homogeneous mass of the required consistency without lumps is formed and process.</li> <li>The duration of mixing is at least 1.5 minutes.</li> <li>The material that has started to harden must not be diluted with water!</li> </ul>			
tions for processing:	<ul><li>After placing the concrete, it must be covered.</li><li>Do not allow fresh concrete to dry out or freeze.</li></ul>			
Packing:	Paper bags 5 kg / full pallet 200 pcs.			
Storage:	<ul> <li>Protect the packaging from weather conditions, store on wooden pallets in a cool and dry place. Cover torn or opened packaging immediately.</li> <li>Duration of storage in original, unopened packaging – 6 months</li> </ul>			
Utilization:	lation as a building material of r	Dispose of hardened mixture in accordance with the requirements of local legislation as a building material of mineral origin.  Dispose of the packaging in accordance with local legislation.		
Safety information:	· ·			
Additional information:	otect from sunlight, drafts, frost and excessively			

Colour	Packing 1	Packing 2	Barcode
Grev	5 kg	200 pcs. / Pallet	4751006560581

The information provided in the technical data sheet refers to the use of the given product in the absence of other technical documentation prepared and issued by the manufacturer. The manufacturer is not responsible for damages caused by improper use of the given product. In case of questions and uncertainties, please contact the manufacturer or seller. Information about the safety of the product is available in the safety data sheets, declared value – in declaration of performance.